

MEGAPRENE 40

Polyurethane Elastomeric Fuel and Chemical Resistant Sealant Pourable and Gunning Grades

Megaprene 40 is a two component polyurethane elastomer based sealant which is recommended for use in moving joints in bridges, reservoirs, dams, pits, channels, sewerage treatment schemes and tanks. Due to its fuel and chemical resistance it is also suitable for sealing joints in car parts. Megaprene 40 complies with the requirements of Australian standard AS 1527-1974 on masonry surfaces. The sealant is resistant to wide range of chemicals, water, U.V, oils and solvents.

Product Specification

Pot life	:	2 hours @ 25°C
Cure Time	:	Initial cure – 6 hours @ 25°C, full cure takes 7 days.
Colour	:	Black
Modulus of Elasticity	:	0.10 MPa
Hardness (shore A)	:	40 @ 25°C
Adhesion	:	Excellent to concrete, brick and other masonry materials.
Temperature	:	Suitable for operating temperatures -20°C to 60°C
Chemical Resistance	:	Resistant to alkalis occurring in building construction when fully cured, also petrol, Skydrol hydraulic fluid, aviation fuels, xylol, 10% sulphuric acid, raw sugar, acetic acid 10%.



VIVACITY ENGINEERING PTY. LTD.

3 Sefton Road, Thornleigh, NSW 2120 • P.O. Box 71, Hornsby, NSW Australia, 1630
Telephone +61-2-9875 3044 Fax +61-2-9875 3665 email:info@megapoxy.com
www.megapoxy.com A.B.N. 78 305 545 664

Application Data

Joint Design : The maximum permanent expansion must not be more than 25% of the joint width. For joints less than 12mm wide the permanent joint movements must not be more than 20%. Maximum joint width 30mm.

Joint Preparation : Surfaces must be sound, free from dirt, grease and all other contaminants. Use backer rod to adjust joint width to depth ratio of 2:1. For joints below 12mm width the ratio should be 1:1. The minimum depth must not be less than 8mm. Do not apply sealant to oily surfaces, bitumen or tar impregnated materials. Cover edges of joint with masking tape.

Priming : Use Megaprene 40 Primer. This is a two part epoxy resin based primer. Mix part 'A' and part 'B' together for two minutes and apply by brush to joint side surfaces. Avoid applying primer to backing material. Allow Megaprene 40 Primer to become touch dry (3-4 hours before applying the sealant).

Sealant Application : Megaprene 40 is supplied as a two component kit with pre-metered part 'A' (base) and part 'B' (hardener). Transfer all of the contents of the hardener (part 'B') into the part 'A' (base) and mix thoroughly by using a power drill fitted with a stirrup stirrer. Mix at slow speed for minimum of 5 minutes moving the stirrer up and down to scrape the sides and bottom of the container. Avoid beating or whipping of air. Hand mixing should not be undertaken as it is likely to result in under-mixing which will prevent proper curing. Megaprene 40 is then ready for application into the joint cavity.

Packaging

Megaprene 40 Pourable	4 litre kit
Megaprene 40 Gun Grade	3.4 kg kit (2.5 lt)
Megaprene 40 Primer	600ml kit

Cleaning

Uncured Megaprene 40 can be removed by Megapoxy thinners, however if cured, mechanical abrasion may be necessary.

Storage

The sealant should be stored in a cool dry place. Shelf life of both Megaprene 40 Pourable and Gun Grade is 1 year from manufacture.

Safety Precautions

Avoid prolonged contact with skin, wash affected areas with soap and warm water. Please for further information please refer to MSDS.

The information presented in this bulletin doesn't imply any warranty. Further, the manufacturer reserves the right to alter this product, the specification and /or the application technique as described herein without prior notice, in line with the manufactures policy of technological advancement and product improvement.